



材料暨工程實驗室-台中

# 試驗報告



報告編號：TV-20-01539

頁數：1 OF 1

報告日期：109年05月18日

主辦機關：保旺事業股份有限公司  
 委託單位：保旺事業股份有限公司  
 地址：雲林縣斗六市雲科路二段109號  
 供料廠商：保旺事業股份有限公司  
 樣品名稱：EVA發泡  
 送驗廠商：保旺事業股份有限公司  
 收件日期：109年04月22日  
 試驗日期：109年04月22日~109年05月18日  
 備註：1.以上資料由顧客提供(收件及試驗日期除外)  
 2.除非另有說明，此報告結果僅對測試之樣品負責  
 未經本公司事先書面同意，此報告不可部分複製  
 3.下述報告內容標示#處由顧客提供


## 試驗結果：

試驗項目	試驗方法	試驗結果	#要求值		
			防焰一級	防焰二級	防焰三級
防焰性試驗	CNS 7614(1994) A 法	----	防焰一級	防焰二級	防焰三級
#火源加熱時間(sec)		10	----		
餘焰時間(sec)		0.0	≤1	≤5	≤5
餘燼時間(sec)		0.0	≤60	≤60	≤60
炭化長度(cm)		4.8	≤5	≤10	≤15

- 註：1.樣品平均厚度 6.0 mm  
 2.測試面為正面  
 3.本試驗報告之試驗地點同實驗室地址

----- oOo -----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

  
 報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.