

Material & Engineering Laboratory-Taichung

TEST REPORT

REPORT NO. TV-16-01216XA

PAGE NO. DATE

1 OF 3 Apr. 22, 2016

Applicant

PROWANG PLASTIC CO., LTD

Address

NO. 55, FENGTIAN RD., DAPI SHIANG, YUNLIN COUNTY 63147, TAIWAN

Product Description

PVC Corrugated Foam Board, PVC Corrugated Roof Board,

PVC Foam Cladding Wall

Product Color

Silver White

Manufacturer

PROWANG PLASTIC CO., LTD

Supplier

PROWANG PLASTIC CO., LTD

Product Submitted By

PROWANG PLASTIC CO., LTD

Received Date

Mar. 29, 2016

Tested Date

Mar. 29, 2016~Apr. 22, 2016

Remark

The information mentioned in the above section is provided by Client

(Exclude Date of Sample Received and Date of Testing)

Test Item:

- 1. UL94 Flammability Test
- 2. Flammability Test

Test Method:

- 1. UL94 (2013) Test for Flammability of Plastic Materials for Parts in Devices and **Appliances**
- 2. CNS7614(1994)Method of Test for Flammability of Thin Material

Test Result:

- PLEASE SEE ATTACHED SHEETS -

The required specification(s) offered in this test report is/are for reference only. The conformity judgment is at the Applicant's final verdict.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWB 8 9 1 9 5 0 2



Material & Engineering Laboratory-Taichung

TEST REPORT

REPORT NO. TV-16-01216XA

2 OF 3 PAGE NO.

DATE

Apr. 22, 2016

Test Item: UL94 Flammability Test

Test Result:

Conditioning 1 : $(23\pm2^{\circ}\text{C and } 50\pm5\% \text{ R.H for } 48 \text{ hours})$:

Criteria conditions	Specimen					Requirements		
	1	2	3	4	5	V-0	V-1	V-2
Thickness(mm)	5.48	5.21	5.38	5.48	5.46	-	-	-
After flame time for each individual specimen t ₁ (sec)	0	0	0	0	0	≤10sec	≤30sec	≤30sec
After flame time for each individual specimen t ₂ (sec)	0	0	0	0	0	≤10sec	≤30sec	≤30sec
Total after flame time (t ₁ plus t ₂ for the 5 specimens) (sec)	0					≤50sec	≤250sec	≦250sec
After flame plus afterglow time for each individual specimen after the second flame application(t_2+t_3) (sec)	0	0	0	0	0	≦30sec	≤60sec	≤60sec
After flame or afterglow of any specimen up to the holding clamp	No	No	No	No	No	No	No	No
Cotton indicator ignited by flaming particles or drops	No	No	No	No	No	No	No	YES

Conditioning 2: $(70\pm1^{\circ}\text{C} \text{ for } 168 \text{ hours}, \text{Cooling 4h at Room temp.})$:

Criteria conditions		Specimen					Requirements		
Criteria conditions	1	2	3	4	5	V-0	V-1	V-2	
Thickness(mm)	5.41	5.45	4.48	5.52	5.24	-	-	_	
After flame time for each individual specimen t ₁ (sec)	0	0	0	0	0	≤10sec	≦30sec	≦30sec	
After flame time for each individual specimen t ₂ (sec)	0	0	0	0	0	≤10sec	≦30sec	≦30sec	
Total after flame time (t ₁ plus t ₂ for the 5 specimens) (sec)	0					≤50sec	≤250sec	≦250sec	
After flame plus afterglow time for each individual specimen after the second flame application(t_2+t_3) (sec)	0	0	0	0	0	≦30sec	≤60sec	≦60sec	
After flame or afterglow of any specimen up to the holding clamp	No	No	No	No	No	No	No	No	
Cotton indicator ignited by flaming particles or drops	No	No	No	No	No	No	No	YES	
2									

The required specification(s) offered in this test report is/are for reference only. The conformity judgment is at the Applicant's final verdict.

Signed for and on

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWB 8 9 1 9 5 0 1



Material & Engineering Laboratory-Taichung

TEST REPORT

REPORT NO. TV-16-01216XA 3 OF 3 PAGE NO.

DATE

Apr. 22, 2016

Test Item: Flammability Test

Test Result:

N.280-24 T								
Test Item	Test Method	Result	Specified					
Flammability Test			Anti-Flaming	Anti-Flaming	Anti-Flaming			
			Grade 1	Grade 2	Grade 3			
Flame heating time (sec)	CNS 7614(1994)	10						
Remaining Flame(sec)	Method A	0.0	≦1	≦5	≦ 5			
Afterglow(sec)		0.0	≦ 60	≦ 60	≦ 60			
Length of Carbonization(cm)		3.5	≦5	≦ 10	≦ 15			

Note: 1.UL94 Flammability Test is subcontracted to SGS M&E Laboratory-Taipei.

2.Flammability Test specimen average thickness:5.2mm

3. This Test Report is an additional original report of TV-16-01216X, Issued date: Apr. 22, 2016.

The required specification(s) offered in this test report is/are for reference only. The conformity judgment is at the Applicant's final verdict.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.